



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
	PRODUCT DESCRIPTION			
Surface treatment	-	-	-	-
Surface complex	-	-	-	D-Max <small>PERFORMANCE</small>
Foam	-	-	-	CXP HD <small>COMFORT</small>
Thickness	EN 428	-	mm	6.2 mm
Weight	EN 430	-	kg/m ²	6.2
Length	EN 426	-	lm	26.4 max
Width	EN 426	-	lm	1.5
	SPORT PROPERTIES			
Shock absorption	EN 14808	≥ 25	%	
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	Class 5 (Fast)
	TECHNICAL CHARACTERISTICS			
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
	CLASSIFICATION			
Fire	EN 13501-1	-	-	
Treatment	-	-	-	Sanosol <small>HYGIENE</small>
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99.9 % inhibits growth
	DECLARATION OF PERFORMANCE			
	DOP-005-1023-A	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	INSTALLATION METHODS		
	Gerflor's recommendation	Unit	Results
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolsport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)

COLOUR RANGE		
 6118 Paris	 6504 London	 6473 New York
 6478 Purple	 6471 Melbourne	Customized lengths

(3) The implementation of an effective cleaning method is the best defence against infection



Health & Safety Life Cycle Analysis

ISO 14001

Recycling