



DESCRIPTION		COMFORT	
Total thickness	EN 428	mm	3,35
	ASTM F386-02	inch	0,13
Wearlayer thickness	EN 429	mm	0,65
	ASTM F410-02	inch	0,03
Weight	EN 430	g/sq.m	2825
		lbs/sq.ft	0,58
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	25
	-	feet - inch	82'
CLASSIFICATION			
Norm / Product specification	-	-	EN 651
	ASTM F1303-04	-	in progress
European classification	EN 685	class	34 - 42
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance (1)	DIN 51 130	class	R10
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649 - EN 651	-	T
Type binder content	ISO 10582	typ	-
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (requirement)	EN 433	mm	≤ 0.20
Residual indentation (measure)	EN 433	mm	≈ 0.08
Impact sound insulation	EN ISO 717-2	dB	19
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protocolsol®
Chemical products resistance (2)	EN 423	-	OK
Treatment	-	-	Sanosol®
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196		> 99,9 % inhibits growth
ENVIRONMENT / INDOOR QUALITY AIR			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 70
Certification			Floorscore™
CE MARKING			
	EN 14041		

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges.

(2) Regarding the resistance to chemicals, please download the corresponding leaflet from our web-site.

(3) The implementation of an effective cleaning method is the best defence against infection