

SUITE 1100

TECHNICKÉ PARAMETRE

Manufacturing process			tufted 1/8" cross over
Total height		mm	± 11,0
Effective pile height		mm	± 8,0
Width		cm	± 400
Total weight		g/m ²	± 2400
Pile weight		g/m ²	± 1100
Number of knots		number / m ²	± 113 400
Pile composition			80% WO 20% PA
Primary backing			woven
Secondary backing			SB/FS
Classification	EN 1307-2004	class	23-32
Fire behaviour	EN 13 501-1	class	C_{fl}-s1
Impact sound insulation	ISO 140/8 1997	dB	± 27
Sound absorption α_s	ISO 354	1000 Hz	± 0,39
Sound absorption α_w	ISO 11654		± 0,25
Thermal retention	DIN 52612	m ² /kW	± 0,098
Lightfastness	ISO 105 B02 2000		≥ 5
Waterfastness change in colour	ISO 105 E01 2002		≥ 4
Rubbingfastness wet	ISO 105 X12 2001		≥ 4
Rubbingfastness dry	ISO 105 X12 2001		≥ 4

SB/FS = synthetic backing fire-safe